



www.rustins.co.uk

## PRODUCT DATA SHEET

<b>Product</b>	<b>Plastic Floor Coating</b>
<b>Type</b>	A two-part cold cure finish, based on Urea Formaldehyde resins, plasticised with alkyd. The finish is highly durable, resistant to impact, abrasion and solvents.
<b>Intended Use</b>	Bare wood, hardboard, MDF, unsealed cork, laminate flooring, slate, stone and vinyl tiles. <b>For use on interior floors only.</b>
<b>Special Features</b>	Quick-drying. Non-yellowing on ageing. Tough, chemically resistant finish. Enhances the colour of the wood. The coating is almost colourless, but some woods change colour when coated. <b>See product packaging for further information.</b>
<b>Preparation</b>	The surface must be clean, smooth, dry and free from wax, dust and contaminants. <b>Read the full instructions on the tin.</b> Our sheet on renovating floors contains further information. Nail holes and small cracks may be filled with <b>Rustin's Woodstopping</b> . Bare wood may be dyed before coating with either <b>Rustin's Floor Dye or Wood Dye</b> . Other brands of dye, stain or paints may be incompatible. Do not apply Knotting or Sanding Sealer.
<b>Mixing</b>	Add the Hardener to the container of Coating and stir well. The mixing ratio is 1 part Hardener to 16 parts Coating. Once mixed, use within 8-10 hours.
<b>Application</b>	Using a large brush or varnish roller, apply evenly and liberally, finishing in the direction of the grain. <b>Rustin's Plastic Coating Thinners</b> may be added to aid the application in hot weather. No other thinners may be added to the coating.
<b>Coats</b>	2 coats are usually sufficient on hardwood floors, but in heavy traffic areas, apply 3 coats. Softwoods and cork may require a minimum of 3 coats, depending on the absorbency. Commercial premises may require 4 coats.
<b>Drying Time</b>	The coating is generally touch-dry within 30 minutes – 1 hour, depending on the temperature.
<b>Re-coating Time</b>	May be re-coated once the previous coat is touch-dry.
<b>Application Temp.</b>	Ideally 15-25°C. Do not use below 15°C, or in conditions of high humidity.
<b>Coverage</b>	13-15 sq.m per litre, 1 coat, depending on the absorbency of the wood.
<b>Maintenance</b>	The coating will accept light foot traffic 2 hours after the final coat and will take 7 days to fully harden. During this period, it should be protected from heavy wear and spills. Afterwards, the surface may be kept clean by mopping with a mild detergent solution. To restore the gloss, use <b>Rustin's Floor Shine</b> . Worn areas may be re-coated once cleaned and sanded, to provide a key. It is not necessary to re-coat the whole floor.
<b>Compatibility</b>	The coating may be used over <b>Rustin's Woodstopping, Wood Dye or Floor Dye</b> and wood may be bleached before coating, with <b>Rustin's Wood Bleach</b> . <b>Important.</b> If any other products are used, such as timber treatments or other brands of dye, stain or paints, these must be tested first for compatibility.
<b>Settlement</b>	STIR WELL BEFORE AND DURING USE. Satin finishes may dry glossy if not stirred.
<b>Shelf-life/Storage</b>	Many years if stored in original, tightly closed containers in normal conditions.
<b>Hazards</b>	Highly flammable. Keep away from sources of ignition- no smoking. Avoid contact with skin and eyes. Do not empty into drains. Wear suitable gloves. Keep container tightly closed. A full Safety Data Sheet is available upon request.
<b>Clean-Up</b>	Clean equipment immediately after use with <b>Rustin's Plastic Coating Thinners</b> or <b>Rustin's Cellulose Thinners</b> , as once hardened, the coating cannot be removed.
<b>Sizes</b>	1 litre      4 litre      Gloss or Satin