

Technical leaflet

Wood preservation

impralan®-End-grain Sealer

Water-borne sealer protecting end-grain surfaces against humidity.

Fields of application	Colourless sealer protection end-grain surfaces against humidity.
Characteristics	Reliable prevention of humidity absorption
	Quick-drying
	Easy to apply
	Good adhesion of following impralan® coatings
	Density approx. 1.0 g/cm³ at 20℃.
Composition	Acrylate dispersion, water, glycols, additives, preserving agents.
Colour	0000-colourless.
Pack size	0,25 litres, 0.75 litre and 2.5 litres.
Application method	Brushing
Application rate	Approx. 200-400 ml/m² depending on absorption capacity of surface.
Application recommendations	Before glueing apply protective sealer with brush with short bristles. Only apply on end-grain surfaces. If applied on other surfaces discolorations may occur. Do not apply and dry at temperatures of less than +10℃ (product, surface and air)
Drying time	Under normal conditions (65% relative air humidity / 20℃) can be re-coated after approx. 4 hours.
	High air humidity and low temperatures delay drying.
Cleaning tools	Rinse with water immediately after use.
Regulation on hazardous material	The product is not subject to specific labelling under current EU regulations.
Precautions	When working with wood preservatives always observe the safety precautions for handling and personal safety. Material Safety Data Sheet available for professionals upon demand.
Storage/ Transport	Cool, but not exposed to frost, can be stored for at least 1 year. Reseal opened containers tightly after use. Keep only in the original container, to be handled by competent persons. RID/ADR: Not restricted.

Environmental	Do not allow impralan®-End-grain Sealer to seep into the soil, water or
protection	drainage channels. European waste catalogue no. 08 01 12.

This technical leaflet has been compiled to the best of our knowledge and experience. In view of the large number of applications, we are unable to give a guarantee for every case. In cases of doubt, our technical department should be contacted for further advice.

Verbal agreements and assurances warrant written confirmation.

This technical leaflet supersedes all preceding ones.

604015GB/ 2010-02-03