



TECHNICAL DATA SHEET

PRODUCT: **Lacquer**

PRODUCT DESCRIPTION

An ultra hard, high quality, acrylic, sandable coating with a gloss finish. This coating dries to a crystal clear film with extremely good sanding properties allowing a very high quality of finish to be obtained. Polyvine Lacquer is specially formulated to bond to a wide range of surfaces. Wood, metal, laminate and glass.

SURFACE PREPARATION

Ensure the surface to be coated is clean and free from grease, wax or polish

APPLICATION

Apply 2-3 coats.

Dilute 10% with water to prime porous surfaces.

By good quality synthetic brush, recommended, or by Low-pressure spray.

Rollers are not recommended, stippling may occur. Stir well.

If cissing occurs, rub onto affected area with a damp cloth to break the surface tension and re-apply.

CAUTION

Test finish for adhesion.

When applied over emulsion/latex paint, it is possible that Lacquer can draw certain stains through the paint, which would not otherwise be visible.

Do not apply over uncured oils.

COVERAGE

Approx. 15-20 sq. m per litre. 160-215 sq. ft per US qt.

CLEAN UP

Any equipment used can be cleaned using soap and water before the coating dries. Wipe any excess off surfaces with a damp cloth. Any dried deposits will need a paint stripper to remove them.

FILM PROPERTIES

DRY FILM: Gloss.

DRYING TIME: 1 to 2 Hours @ 20°C / 70°F

Low temperature/high humidity increases drying time.

CURE TIME: Up to 5 days @ 20°C / 70°F

RECOAT TIME: Up to 2 Hours @ 20°C / 70°F

HARDNESS: Highly Durable

NON YELLOWING

NO FIRE HAZARD Before or during use, or in the cured state.

RESISTANT TO: Water and abrasion.

PACKAGING

500ml, 1L, 4L.

STORAGE

Store in unopened containers in a cool dry place away from direct sunlight.

HEALTH SAFETY AND THE ENVIROMENT

Non-hazardous. Ensure good ventilation. Keep out of reach of children. Contact with eyes-wash immediately with warm water. Remove excess from tools and mixing vessels before washing in warm soapy water. Do not empty containers into drains or watercourses.

The information supplied herein is accurate to the best of our knowledge. Since conditions and methods are beyond our control, no warranty is expressed or implied. You are advised to assess the suitability of the product on a test area before application

Further information may be obtained from:

POLYVINE LIMITED

Vine House
Cheddar Business Park
Wedmore Rd.
Cheddar BS27 3EB
United Kingdom

Telephone No. 0845 017 1671
International +44 845 017 1671
Fax: 0845 017 1672
Email info@polyvine.co.uk

Date of issue: August 2015