



GENERAL DESCRIPTION

Junckers BaseFill is a quick-drying fillerbase, which, in combination with Junckers solvent-based or water-based lacquers, is suitable for most sanded and untreated parquet floors, including most exotic wood floors.

Junckers BaseFill is to be mixed with sanding dust from the floor sanding process and should be used only as a filler-base.

PRODUCT DESCRIPTION

Product: Solventborne filler-base to be mixed with wood powder from sanding of the actual floor.

Package sizes: 5 litre and 10 litre.

Appearance: Colourless.

TECHNICAL DATA

Coverage: 10 m² per litre.

Before application: Stir well before use.

Application tools: Broad full-edged spatula of stainless steel.

Substrate temperature: Minimum 15° C.

Dilution: Delivered ready for use. Dilution is not recommended.

Drying time: Dry to touch after approx. 15 min. at 20° C and 50 % RH.

Cleaning of tools: White spirit.

Storage: Lasts for 2 years if unopened and stored at 20° C.

SYSTEM RECOMMENDATIONS

High traffic areas:

1 coat Junckers BaseFill 10 m²/litre
+ 2 coats Junckers HP Commercial 10m²/litre
or
1 coat Junckers BaseFill 10 m²/litre
+ 2 coats Junckers STRONG 10 m²/litre

Low traffic areas:

1 coat Junckers BaseFill 10 m²/litre
+ 2 coat Junckers ProTech 10 m²/litre
or
1 coat Junckers BaseFill 10 m²/litre
+ 2 coat Junckers ProFinish 10 m²/litre

Sport areas:

1 coat Junckers BaseFill 10 m²/litre
+ 2 coats Junckers HP SPORT 10m²/litre

DIRECTION FOR USE

Untreated/sanded floors:

Ensure that the surface is absolutely clean, dry and free from all dust, wax, grease, polish, soap residues etc. Sand the surface to remove dirt and irregularities.

Vacuum thoroughly and mix enough sanding dust into Junckers BaseFill until a thick but spreadable paste is obtained. If too thick adjust with Junckers BaseFill.

Stir well before use and spread the paste quickly using a stainless steel spatula. Sand with sandpaper grit 120-150. Vacuum thoroughly. Proceed according to one of Junckers "System recommendations".

Previously sealed floors:

Use grit 24-36 to strip old coats. Then remove abrasion marks with grit 60-80. Finally, use grit 120-150 to obtain a completely smooth surface. Vacuum sanding dust and prime the floor as described under "Untreated/ sanded floors".

IMPORTANT

Before use of the product, read the label on the container carefully and observe the advised precautionary safety measures.

FURTHER INFORMATION

Products:

F 4.2 - Junckers ProFinish
F 5.1 - Junckers STRONG
F 6.2 - Junckers ProTech
F 8.2 - Junckers HP SPORT
F 8.5 - Junckers HP Commercial